



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁴ : A24D 1/02, D21H 5/16</p>	<p>A1</p>	<p>(11) International Publication Number: WO 88/ 01478 (43) International Publication Date: 10 March 1988 (10.03.88)</p>
<p>(21) International Application Number: PCT/GB87/00604 (22) International Filing Date: 27 August 1987 (27.08.87) (31) Priority Application Numbers: 8620698 8715849 (32) Priority Dates: 27 August 1986 (27.08.86) 6 July 1987 (06.07.87) (33) Priority Country: GB (71) Applicant (for all designated States except US): GALLAHER LIMITED [GB/GB]; Members Hill, Brooklands Road, Weybridge, Surrey KT13 0QU (GB). (72) Inventors; and (75) Inventors/Applicants (for US only) : ADAMS, Brian [GB/GB]; 11 Mount Pleasant Road, Jordantown, Newton Abbey (GB). CUNNINGHAM, Linda [GB/GB]; 13 Marlborough Park, Lurgan, Co. Armagh (GB).</p>		<p>(74) Agent: LAWRENCE, Peter, Robin, Broughton; Gill Jennings & Every, 53/64 Chancery Lane, London WC2A 1HN (GB). (81) Designated States: AT (European patent), AU, BE (European patent), CH (European patent), DE (European patent), FR (European patent), GB (European patent), IT (European patent), JP, LU (European patent), NL (European patent), SE (European patent), US. Published With international search report.</p>
<p>(54) Title: SMOKING ROD WRAPPER AND COMPOSITIONS FOR THEIR PRODUCTION</p> <p>(57) Abstract</p> <p>A wrapper for a smoking rod comprises a permeable substrate carrying a discontinuous coating of a porosity-reducing composition such that, in the coated area, the porosity of the wrapper is less than two thirds of the porosity of the uncoated substrate.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	ML	Mali
AU	Australia	GA	Gabon	MR	Mauritania
BB	Barbados	GB	United Kingdom	MW	Malawi
BE	Belgium	HU	Hungary	NL	Netherlands
BG	Bulgaria	IT	Italy	NO	Norway
BJ	Benin	JP	Japan	RO	Romania
BR	Brazil	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	LI	Liechtenstein	SN	Senegal
CH	Switzerland	LK	Sri Lanka	SU	Soviet Union
CM	Cameroon	LU	Luxembourg	TD	Chad
DE	Germany, Federal Republic of	MC	Monaco	TG	Togo
DK	Denmark	MG	Madagascar	US	United States of America
FI	Finland				

Smoking Rod Wrapper and Compositions
for their Production

It is well known that the burn and smoke
5 characteristics of a smoking rod are affected by the
porosity of the rod wrapper. The wrapper typically has
a porosity of, for instance, down to about 20 Coresta or
up to, for instance, about 200 Coresta.

It is known to obtain special effects as a result of
10 perforating certain regions of the wrapper, this
perforation generally giving the wrapper a porosity above
1,000, for instance 5,000 to 7,000, Coresta. In order
to defer the effect of these perforations it is known to
block the perforations with a material that is intended
15 to unblock the perforations as the burning tip approaches
them. See for instance U.S. 2,992,647, 3,511,247 and
3,526,904 and GB 1,439,778. Although these compositions
may be such as to permit the perforations to open as the
burning tip approaches they do have the effect of
20 rendering the wrapper, where there are no open
perforations, substantially wholly impermeable.

The present invention relates primarily to
unperforated wrappers, e.g., wrappers typically having
porosity values below about 200 Coresta. With such
25 unperforated wrappers it is known that reduced porosity
can result in increased tar delivery, increased puff
number and increased carbon monoxide delivery. The
increased tar can be desirable as it gives an improved
sensation to the smoker. The increased puff number
30 tends to be undesirable as (unless the tar is increased
sufficient to compensate) the smoke is likely to appear
weak. Increased carbon monoxide is undesirable,
particularly when the ratio of carbon monoxide:tar is
increased.

In U.S. 3,911,932 a wrapper having an initial porosity of about 15 to 30 Coresta (60 to 20 seconds Greiner) is coated at the burning cone end with a film-forming, porosity-reducing additive to give a
5 porosity of around 5 Coresta (120 to 300 second Greiner).

The material that is coated at the burning tip is applied as a continuous coating and the porosity-reduction due to this material will persist substantially up until the moment when the wrapper coated
10 with the material is burnt.

It is also suggested in U.S. 3,911,932 that it can be desirable to have an intermediate zone of medium porosity between the low porosity cone end and the higher porosity mouth end, the intermediate zone having a
15 porosity of 6 to 18 Coresta (120 to 60 seconds Greiner). It can be achieved by applying the porosity-reducing material in a solution that is sufficiently dilute that the solution forms a discontinuous film on the substrate whereas at the cone end a continuous film is formed, so
20 as to give less porosity.

The purpose of reducing porosity near the burning tip is to increase the tar in the smoke. Unfortunately it also increases the carbon monoxide and, in particular, can increase the ratio of carbon monoxide to tar. The
25 low porosity at the burning tip inhibits free burn (burn of the rod when air is not drawn through the rod by the smoker).

With conventional smoking rods, there is a tendency for the tar delivery in the later puffs to be
30 considerably higher than in the earlier puffs. As a result the smoking sensation in the early puffs is relatively weak and if the total tar delivery is increased, so as to give stronger earlier puffs, this inevitably leads to an even higher tar delivery in the
35 later puffs. It would be desirable to be able to alter

the profile of the tar delivery, so that there is less difference between the early and late puffs, and to do this without having adverse effects on other smoking properties. It would also be desirable to be able to
5 increase tar delivery without having an adverse effect on other smoking properties and, in particular, without increasing the ratio of carbon monoxide:tar and without significantly increasing the puff number of the smoking rod.

10 In the invention a smoking rod wrapper material comprises a permeable substrate having a coated area in which the material is coated or impregnated with a coating of porosity reducing porosity-reducing substance, and the material is characterised in that the coating is
15 discontinuous and the porosity of the material in the coated area is (measured in coresta) less than two thirds the porosity of the uncoated substrate. Thus the porosity in coresta of the coated area is less than about 67% of the porosity in coresta of the substrate in the absence of
20 the discontinuous coating or, expressed on an alternative basis, the porosity of the uncoated substrate is at least 50% greater than the porosity of the coated substrate.

Throughout this specification we refer to the substrate as being coated or uncoated and to the porosity
25 reducing substance being present as a coating to form a coated area, but it should be understood that the porosity reducing substance may either be on the surface as a true coating or some or all of it may be impregnated into the substrate.

30 Generally the porosity in the coated area is below about 50% the porosity of the uncoated substrate. If the porosity in the coated area is too low then it is difficult to obtain the required balance of properties and so usually the porosity in the coated area is at
35 least about 5 or 10%, and often at least about 20%, of

the porosity of the uncoated substrate. Generally the porosity in the coated area is about 25 to about 50% of the porosity of the uncoated substrate, i.e. the uncoated substrate has a porosity 2 to 4 times the coated
5 substrate. All these porosity values are measured in coresta.

Since the coating is discontinuous it consists of coated and uncoated regions within the coated area. The porosity of the substrate in the uncoated regions is
10 higher than the porosity of the coated regions and the porosity in the uncoated regions is often close to or the same as the porosity of the initially uncoated permeable substrate.

The provision of uncoated regions in this manner
15 within the coated area is desirable since it can permit sufficient ventilation through the coating, especially in the critical 10mm, or possibly 20mm, behind the burning cone to give beneficial free burn properties, and this greatly improves the overall smoking performance of the
20 smoking rod.

If the size of the uncoated regions in the coated area is too small then they will give inadequate benefit, and for this reason the uncoated regions within the coated area should generally be at least 5%, and
25 preferably at least 10%, and often at least 15%, of the coated area. If the regions are too large then the discontinuous coating will not reduce the permeability of the substrate sufficiently and the permeability of the coated substrate will, instead, be controlled primarily
30 by the permeability of the uncoated regions. Accordingly the uncoated regions should normally cover less than 50%, generally less than 30% and most preferably less than 20%, of the coated area. Best results are generally obtained when the uncoated regions
35

within the discontinuous coating cover around 10 or 15% to 20% of the area of that coating.

It is generally desirable that, within the coated area, the material should have substantially uniform properties and so generally the uncoated permeable substrate has substantially uniform porosity properties throughout its surface area and the uncoated regions are preferably distributed substantially uniformly throughout the coated area.

10 The discontinuous coating may be applied in any manner that permits the desired controlled porosity, but preferably it is applied by printing, preferably in a pattern. The printing pattern can be in any suitable form but is preferably in the form of dots that
15 preferably have a diameter of from 0.3 to 3mm, generally 0.5 to 2mm and most preferably about 1mm. The dots may be circular but are preferably substantially square. The separation between the dots is preferably from 0.03 to 0.3mm, most preferably around 0.05 to 0.2mm, with best
20 results generally being obtained at around 0.1mm.

Since the discontinuous coating reduces porosity it is desirable to include a burn promoter in the wrapper material so as to improve the balance of burn properties, and in particular so as to provide the material with a
25 puff number that is not substantially greater than the puff number of the material if it was not provided with the coating.

Suitable burn promoters are well known and include alkali metal (generally sodium or potassium) salts of
30 organic acid (generally citric acid or tataric acid), or potassium nitrate.

The burn promoter may be applied uniformly throughout the material, e.g., by impregnation into the wrapper in conventional manner. This is generally
35 suitable when the coated area has a porosity of, for

instance, above about 20 Coresta (and generally when the uncoated substrate has a porosity above about 80 Coresta) since adequate results can then be achieved with relatively low additions of burn promoter, typically 0.2 to 2%, generally about 1% (percentages are based on the weight of the substrate, which is typically about 40mg in a typical wrapper).

When the coated paper has a lower porosity (typically below 15 Coresta) and/or the uncoated paper has a porosity below 80 Coresta, larger amounts of burn promoting additive may be required to give adequate puff number, typically 2 to 10%, e.g., about 5%. These higher percentages can affect the taste and can increase tar delivery and so for these less porous wrappers it is particularly preferred to apply the burn promoter only in the coated area, and preferably to include it in the porosity-reducing composition. The amount of burn promoter may be from 5 to 50% generally 10 to 40% of the dry weight of the composition. It can be convenient to include the burn promoter in the discontinuous coating for all the wrapper materials of the invention.

Apart from the burn promoter, the porosity-reducing composition is preferably free of anything that will have significant organoleptic properties since the coating is generally present solely to alter the porosity and is not present primarily to provide an artificial additive to the smoke.

The porosity-reducing composition may be formed substantially only (e.g. above 80%, preferably above 90% dry weight) of a polymeric binder, and optionally burn promoter. Additives for adjusting rheology and other print characteristics may be included as necessary. The polymeric material may be a starch or cellulose polymer or derivative, for instance hydroxy-ethyl or -propyl cellulose, carboxy methyl cellulose or ethyl cellulose,

or it may be a synthetic polymer, for instance polyvinyl alcohol or, preferably, ethylene vinyl acetate copolymer. Instead of using a polymeric binder, a material that will melt or volatilise during use, for instance as described in EP231664, can be used. Thus the composition can comprise 0 to 20% polymeric binder, optionally a burn promoter, and 80 to 100% of a non-polymeric material that melts or volatilises at 30 to 150%, preferably being a fatty acid salt or alcohol.

10 The permeable substrate is preferably an unperforated wrapper substrate of typical fibrous constitution and which has not been given any coating other than the discontinuous coating of the invention. However it may additionally be perforated and may have
15 been given a continuous coating as described in EP231664, in which event the uncoated permeable substrate that is provided with a discontinuous coating in the invention is the coated, perforated, substrate of EP231664.

The discontinuous coating of the invention can
20 extend along the entire length of the smoking rod but preferably extends only part way along the rod. Typically the coated area covers 40 to 80% of the total area of the wrapper (generally excluding any wrapper around a filter). The coated area may extend 40 or 50 to
25 95%, generally 50 to 85% and most preferably around 60 to 75%, of the length of the rod from the cone end towards the mouth end. For instance a typical rod having a burning length of about 75mm may be coated for from about 30 to 65cm, preferably 40 or 50 to 65mm, generally about
30 60mm, from the burning tip end. Alternatively the coated area can extend part way from the mouth end towards the cone. Generally it extends at least 5%, preferably at least 15% and most preferably at least 30%, of the distance from the mouth end towards the cone but
35 generally less than 60% and preferably less than 50% of

the distance. Typically the coating extends for at least 10mm, and usually 20 to 50mm, preferably 30 to 40mm from the mouth end.

The total amount of coated porosity-reducing composition (dry weight) is generally below 1, and generally below 0.6 and often below 0.5, mg/cm² since such amounts are normally sufficient to achieve the desired low porosity values and it is unnecessary to add additional material. The amount is usually at least 0.1, and generally at least 0.2mg/cm², since lower amounts may be inadequate to impart the desired porosity values. These amounts are considerably less than the rates of coating that have been used previously for printing active smoking ingredients on to wrappers, e.g., as described in GB 2,094,611. Despite the higher loadings, the distribution and size of the printed dots in GV 2094611 did not result in useful reduction of porosity.

The total loading of porosity reducing composition (dry weight) is generally below 4mg and preferably below 3.5mg. When it is applied at the burning tip end it is usually at least about 2 or 2.5mg but can be less, e.g., below 1mg and as low as 0.7 or even down to 0.3mg, if it is applied at the mouth end.

Discontinuous coatings are generally applied by printing, preferably by gravure. The porosity-reducing material is generally applied as a dispersion or, preferably, as a solution in a solvent that is then evaporated. The solvent may be water or aqueous organic, generally alcoholic, solvent but is preferably a substantially non-aqueous alcohol or other organic solvent.

The invention includes also continuous sheets of wrapper material having uncoated areas and areas coated with a porosity-reducing substance all as described

above, with the areas being arranged such that wrappers as defined above can be cut from the sheets. For instance there may be transverse or longitudinally arranged bands of coated material separated by bands of
 5 uncoated material, each type of band either being of the width for one wrapper or being of a width for two wrappers (arranged with two adjacent coated areas separated by two adjacent uncoated areas).

The following are some examples.

10 Example 1

Three cigarette rod wrappers having initial porosities of 50, 80 and 135 Coresta respectively were printed by a composition of 30% ethylene vinyl acetate in ethanol to give a pattern of dots having a diameter of
 15 1mm covering 60% of the surface of the printed area which extended 65mm from the cone end of the rod. The porosity, puff number, delivery of tar and delivery of carbon monoxide was recorded for each of the uncoated papers (control) and for the printed samples and the
 20 results are shown in Table 1.

Table 1

	50 Coresta		80 Coresta		135 Coresta	
	Control	Sample	Control	Sample	Control	Sample
25 Porosity (Coresta)	47	15	78	20	118	46
Puff No.	10.0	10.3	10.3	10.8	10.5	11.1
Tar mg	10.2	12.31	10.0	12.25	9.9	10.89
30 CO mg	10.3	13.4	9.6	12.7	7.4	9.45

This clearly shows that the samples of the invention can give increases tar yield with significantly adversely
 35 effecting the tar: Co ratio.

Example 2

Paper having a porosity of 135 Coresta impregnated with 1% (based on the weight of paper) sodium citrate was printed over an area of 12cm² extending from the cone end
5 (about 60% of the length of the rod) with square dots having a side length of 1mm and a separation between the sides of 0.1mm and formed of ethylene vinyl acetate copolymer in an appropriate carrier. The printed paper had a porosity of 30 Coresta.

10 The smoking performance of the sample wrapper according to the invention, carrying the discontinuous coating, and a control wrapper of the same substrate but without the discontinuous coating, was assessed. The puff number and the weight of tar in mg (total particulate
15 matter) was recorded for the sample and for the control for each puff, and the percentage change in tar in each puff was recorded. The results are shown in table 2.

20

25

30

35

	PUFF NO.	SAMPLE TAR mg	CONTROL TAR mg	%CHANGE
5	1	0.52	0.52	0
	2	0.72	0.62	+16
	3	0.88	0.77	+14
	4	0.96	0.99	-3
10	5	1.14	1.22	-7
	6	1.12	1.38	-18
	7	1.30	1.68	-23
	8	1.46	1.79	-18
	9	1.60	2.04	-21
15	10	1.31	0.09	-

Thus by the invention it is seen that this particular construction of cigarette has permitted the tar delivery profile to be more uniform when using the printed wrapper of the invention than the unprinted control, with a relative increase in the tar delivery in the early puffs and relative decrease in the later puffs.

In the following examples this change in profile is indicated by the "tar ratio" which is the ratio of the amount of tar in the last full puff to the amount of tar in the first full puff. The ratio should be as low as possible.

30 Example 3

The process of example 2 was repeated, using 0.15 to 0.3mg/cm² ethylene vinyl acetate copolymer, but the paper had an initial porosity of 30 Coresta, a final porosity of 11 Coresta, and the dry components of the composition that was printed were a 2:1 by weight mixture of ethylene

vinyl acetate copolymer with sodium acetate. The tar ratio was 1.7 for the sample and 2.2 for the control.

Example 4

The process of example 2 was repeated except that the initial paper had a porosity of 30 Coresta, was impregnated with 3% by weight sodium citrate as burn promoter, and was printed with 0.2mg/cm² ethylene vinyl acetate copolymer to give a porosity in the coated area of 8 Coresta. The tar ratio was 1.8 for the sample and 2.2 for the control.

Example 5

The process of example 2 was repeated except that the printed composition consisted primarily of palmitic acid salt as described in EP231664 and was printed in a pattern, as in example 2 but covering approximately half the length of the wrapper from the mouth end. The tar ratio was 1.9 for the sample and 2.2 for the control. Similar results were obtained using octadecanol in place of the fatty acid salt.

20

25

30

35

CLAIMS

1. A smoking rod wrapper material comprising a permeable substrate having a coated area in which the material is coated or impregnated with a coating of porosity-reducing composition characterised in that the coating is discontinuous and the porosity of the material in the coated area is (measured in coresta) less than two thirds the porosity of the uncoated substrate.
2. A material according to claim 1 in which the porosity of the coated area is (measured in coresta) from 25 to 50% of the porosity of the uncoated substrate.
3. A material according to claim 1 in which the uncoated substrate has the porosity of 20 to 200 coresta and the coated area has a porosity of 3 to 60 coresta.
4. A material according to claim 1 in which the uncoated substrate has a porosity of 30 to 150 coresta and the coated substrate has a porosity of below 40 coresta.
5. A material according to claim 1 in which the coated area is 40 to 80% of the coated area of the wrapper.
6. A material according to claim 1 in which the coated area extends from the burning tip end by a distance of from 40 to 85% of the length of the rod or extends from the mouth end by a distance of 15 to 60% of the length of the rod.
7. A material according to claim 1 that includes 0.2 to 10%, by weight of the material, of a burn promoter.
8. A material according to claim 1 in which the coated area has a porosity of at least 20 coresta and the material includes a burn promoter in the coated area in an amount of 0.2 to 2% based on the weight of the substrate.
9. A material according to claim 1 in which the coated area has a porosity of below 15 coresta and the

discontinuous coating includes a burn promoter in an amount of from 2 to 10% by weight of the substrate.

10. A material according to claim 1 in which the composition is substantially free of any organoleptic additive other than burn promoter.

11. A material according to claim 1 in which the amount of the porosity reducing composition is 0.2 to 1mg per cm^2 of coated area.

12. A material according to claim 1 in which, within the coated area, from 5 to 30% is unsubstantially uncoated.

13. A material according to claim 1 in which the porosity reducing composition comprises ethylene vinyl acetate or a fatty alcohol or fatty acid salt.

14. A material according to claim 1 in the form of a warpper around a smoking rod.

20

25

30

35

INTERNATIONAL SEARCH REPORT

International Application No PCT/GB 87/00604

I. CLASSIFICATION OF SUBJECT MATTER (if several classification symbols apply, indicate all) ⁴		
According to International Patent Classification (IPC) or to both National Classification and IPC		
IPC ⁴ : A 24 D 1/02; D 21 H 5/16		
II. FIELDS SEARCHED		
Minimum Documentation Searched ⁷		
Classification System	Classification Symbols	
IPC ⁴	A 24 D D 21 H	
Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in the Fields Searched ⁸		
III. DOCUMENTS CONSIDERED TO BE RELEVANT ⁹		
Category ⁹	Citation of Document, ¹¹ with indication, where appropriate, of the relevant passages ¹²	Relevant to Claim No. ¹³
A	US, A, 3911932 (W.G. HOUCK et al.) 14 October 1975 see claims 1,2,4,9 cited in the application --	1,13
A	DE, A, 2362319 (PHILIP MORRIS INC.) 18 July 1984 see claims 1-4,9-12 & GB, A, 1439778 (cited in the application) --	1,13
A	US, A, 2992647 (F.H.J. FIGGE) 18 July 1961 see claims 1,4; figures 1,9 cited in the application --	1,13
A	US, A, 3511247 (R.A. TAMOL) 12 May 1970 see claim 1 cited in the application --	1,13
A	US, A, 3526904 (R.A. TAMOL) 1 September 1970 see claim 1 cited in the application	1,13
<div style="display: flex; justify-content: space-between;"> <div style="width: 48%;"> <p>¹⁰ Special categories of cited documents: --</p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> </div> <div style="width: 48%;"> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step</p> <p>"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>"&" document member of the same patent family</p> </div> </div>		
IV. CERTIFICATION		
Date of the Actual Completion of the International Search	Date of Mailing of this International Search Report	
11th November 1987	09 DEC 1987	
International Searching Authority	Signature of Authorized Officer	
EUROPEAN PATENT OFFICE	4. VAN MOL	

FURTHER INFORMATION CONTINUED FROM THE SECOND SHEET

A	DE, C, 652124 (SCHOELLER & HOESCH GmbH) 7 October 1937 see claims	1
A	US, A, 3699973 (R.A. TAMOL) 24 October 1974 see claim 1	1,13

V. ☐ OBSERVATIONS WHERE CERTAIN CLAIMS WERE FOUND UNSEARCHABLE ¹

This international search report has not been established in respect of certain claims under Article 17(2) (a) for the following reasons:

1. ☐ Claim numbers because they relate to subject matter not required to be searched by this Authority, namely:
2. ☐ Claim numbers because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:
3. ☐ Claim numbers because they are dependent claims and are not drafted in accordance with the second and third sentences of PCT Rule 6.4(a).

VI. ☐ OBSERVATIONS WHERE UNITY OF INVENTION IS LACKING ²

This International Searching Authority found multiple inventions in this international application as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims of the international application.
2. ☐ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims of the international application for which fees were paid, specifically claims:
3. ☐ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claim numbers:
4. ☐ As all searchable claims could be searched without effort justifying an additional fee, the International Searching Authority did not invite payment of any additional fee.

Remark on Protest

- ☐ The additional search fees were accompanied by applicant's protest.
- ☐ No protest accompanied the payment of additional search fees.

ANNEX TO THE INTERNATIONAL SEARCH REPORT ON

INTERNATIONAL APPLICATION NO. PCT/GB 87/00604 (SA 18381)

This Annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report. The members are as contained in the European Patent Office EDP file on 20/11/87

The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A- 3911932	14/10/75	None	
DE-A- 2362319	18/07/74	NL-A- 7317412	28/06/74
		AU-A- 6361873	19/06/75
		AU-B- 468281	08/01/76
		GB-A- 1439778	16/06/76
		CA-A- 990604	08/06/76
		CH-A- 581962	30/11/76
US-A- 2992647		None	
US-A- 3511247	12/05/70	NL-A- 6906183	12/11/69
		LU-A- 58598	22/08/69
		DE-A- 1923776	21/05/70
		FR-A- 2008201	16/01/70
		GB-A- 1251429	27/10/71
		CH-A- 523029	31/05/72
		BE-A- 732531	16/10/69
US-A- 3526904	01/09/70	NL-A- 6906125	12/11/69
		LU-A- 58592	22/08/69
		DE-A, B, C 1923775	21/05/70
		FR-A- 2008200	16/01/70
		GB-A- 1257360	15/12/71
		CH-A- 514296	31/10/71
		BE-A- 732530	16/10/69
DE-C- 652124		None	
US-A- 3699973	24/10/72	BE-A- 785827	03/11/72

For more details about this annex :
see Official Journal of the European Patent Office, No. 12/82